


# Weight of Sheet Felt

Weight in Lbs. SO. YD. of Sheet Felt



THICK	SOFT 0.40 - 50	MEDIUM 0.52 - 0.58	HARD 0.60 - 0.68	ROCKHARD 0.70 - 0.85
1/8"	2.3 - 2.9	3.0 - 3.4	3.5 - 3.9	4.0 - 4.9
1/4"	4.6 - 5.8	6.0 - 6.8	7.0 - 7.9	8.0 - 9.9
3/8"	7.0 - 8.7	9.0 - 10.2	10.5 - 11.9	12.1 - 14.8
1/2"	9.3 - 11.6	12.1 - 13.5	14.0 - 15.8	16.2 - 19.8
5/8"	11.6 - 14.5	15.1 - 17.0	14.5 - 19.8	20.3 - 24.7
3/4"	14.0 - 17.5	18.2 - 20.3	21.0 - 23.8	24.3 - 29.7
7/8"	16.3 - 20.4	21.2 - 23.6	24.4 - 27.7	28.5 - 34.6
1"	18.6 - 23.3	24.2 - 27.0	27.9 - 31.7	32.6 - 39.6
1-1/2"	27.9 - 34.9	36.3 - 40.5	41.9 - 47.5	48.9 - 59.4
2"	37.3 - 46.7	48.5 - 54.1	55.9 - 63.4	65.3 - 79.3

*\* Please Note: The above information has been carefully reviewed to be as reliable as possible. However, due to the diversity of felt applications we cannot guarantee its accuracy, and urge you to make your own tests to determinate the suitability of a given felt material.*



www.multifeutre.com

# Weight of Felt Polishing Wheels

In various densities



SIZE DIA. THICK	EXTRA SOFT 0.33 - 0.38	SOFT 0.40 - 0.48	MEDIUM 0.52 - 0.58	HARD 0.60 - 0.68	ROCK-HARD 0.70 - 0.85
6" x 1/4"	0.083-0.096	0.100-0.121	0.131-0.146	0.151-0.171	0.176-0.214
6" x 1/2"	0.166-0.192	0.201-0.242	0.262-0.292	0.302-0.342	0.352-0.428
6" x 1"	0.332-0.384	0.403-0.484	0.524-0.584	0.604-0.684	0.704-0.856
6" x 2"	0.664-0.768	0.806-0.968	1.048-1.168	1.208-1.368	1.408-1.712
7" x 1/4"	0.113-0.130	0.137-0.164	0.178-0.198	0.205-0.233	0.240-0.291
7" x 1/2"	0.226-0.260	0.274-0.328	0.356-0.396	0.410-0.466	0.480-0.582
7" x 1"	0.452-0.520	0.548-0.656	0.712-0.792	0.820-0.932	0.960-1.164
7" x 2"	0.904-1.040	1.096-1.312	1.424-1.584	1.640-1.864	1.920-2.328
8" x 1/4"	0.148-0.170	0.179-0.215	0.233-0.260	0.269-0.305	0.314-0.381
8" x 1/2"	0.296-0.340	0.358-0.430	0.466-0.520	0.538-0.610	0.628-0.762
8" x 1"	0.592-0.680	0.716-0.860	0.932-1.040	1.076-1.220	1.256-1.524
8" x 2"	1.184-1.360	1.432-1.720	1.864-2.080	2.152-2.440	2.512-3.048
9" x 1/4"	0.187-0.220	0.226-0.272	0.290-0.328	0.340-0.386	0.396-0.482
9" x 1/2"	0.374-0.440	0.452-0.544	0.580-0.656	0.680-0.772	0.792-0.964
9" x 1"	0.748-0.880	0.904-1.088	1.160-1.312	1.360-1.544	1.584-1.928
9" x 2"	1.496-1.760	1.808-2.176	2.320-2.624	2.720-3.088	3.168-3.856
10" x 1/4"	0.231-0.266	0.280-0.336	0.364-0.406	0.420-0.476	0.490-0.595
10" x 1/2"	0.462-0.532	0.560-0.672	0.728-0.812	0.840-0.952	0.980-1.190
10" x 1"	0.924-1.064	1.120-1.344	1.456-1.624	1.680-1.904	1.960-2.380
10" x 2"	1.848-2.128	2.240-2.688	2.912-3.248	3.360-3.808	3.920-4.760
12" x 1/4"	0.332-0.383	0.403-0.484	0.524-0.585	0.605-0.685	0.705-0.856
12" x 1/2"	0.664-0.766	0.806-0.968	1.048-1.170	1.210-1.370	1.410-1.712
12" x 1"	1.328-1.532	1.612-1.936	2.096-2.340	2.420-2.740	2.820-3.424
12" x 2"	2.656-3.064	3.224-3.872	4.192-4.680	4.840-5.480	5.640-6.848
14" x 1/4"	0.452-0.521	0.548-0.659	0.713-0.796	0.823-0.933	0.960-1.166
14" x 1/2"	0.904-1.042	1.096-1.318	1.426-1.592	1.646-1.866	1.920-2.332
14" x 1"	1.808-2.084	2.192-2.636	2.852-3.184	3.292-3.736	3.840-4.664
14" x 2"	3.616-4.168	4.384-5.272	5.704-6.368	6.584-7.472	7.680-9.328
16" x 1/4"	0.591-0.681	0.716-0.860	0.931-1.039	1.075-1.219	1.254-1.523
16" x 1/2"	1.182-1.362	1.432-1.720	1.862-2.078	2.150-2.438	2.508-3.046
16" x 1"	2.364-2.724	2.864-3.440	3.724-4.156	4.300-4.876	5.016-6.092
16" x 2"	4.728-5.448	5.728-6.880	7.448-8.312	8.600-9.752	10.032-12.184

\* Please Note: The above information has been carefully reviewed to be as reliable as possible. However, due to the diversity of felt applications we cannot guarantee its accuracy, and urge you to make your own tests to determinate the suitability of a given felt material.